

COLOURTHANE SE200 CLEAR POLYURETHANE SEALER

TM6.21

DESCRIPTION

• a clear, two pack polyurethane sealer for interior timber

PRINCIPAL CHARACTERISTICS

- fast curing, with excellent quick sanding time
- designed to give a high build finish to open grained timbers
- suitable for use on substrates stained with Wattyl Craftsman Dye Stain Fast, Slow or Craftsman Pigmented Stain
- excellent hold-out, especially when used under Colourthane S-Series Clear Topcoat

Note: We advise that you must test this product to determine if it is suitable for your particular use.

COLOUR AND GLOSS

• clear, low sheen

BASIC DATA AT 25°C and 50% RELATIVE HUMIDITY

_	mix ratio	1A-1P by volumo
•	IIIIX Tatio	TA. TB by volume
•	dust free	10 minutes
•	touch-dry	20 minutes
•	sandable	2 hours
•	recoat	10 minutes (with itself), 1 hour (topcoats)
•	practical spreading rate	8m²/L
•	shelf life (cool, dry place)	at least 12 months in unopened container

SURFACE PREPARATION

- all surfaces must be free from wax, silicone, oil and other contaminants
- fill holes and minor imperfections with Wattyl Full Stop Timber Putty
- sand smooth with 180-240 grade fre-cut paper, and remove all sanding dust
- if required, stain the surface using Wattyl Craftsman Dye Stain Fast, Slow or Craftsman Pigmented Stain
- Do not use Woodgrain Filler under Colourthane SE200 Clear Polyurethane Sealer

INSTRUCTIONS FOR USE

- mixing ratio by volume: 1A:1B
- cure with Colourthane SE200 Part B only
- induction time- 5 minutes, mix again before using
- potlife at 25°C 2 hours. Do not use after this time even if the mix is still liquid
- stir the components and mixed product well using a mechanical mixer
- For MDF and high resin-content timbers (such as cedar and rosewood), thin 10% with Colourthane Reducer Standard
- apply one coat by conventional spray, may be re-coated immediately with itself after the first coat
- has become dust free, but better hold-out is obtained if re-coating is left for one hour
- may be sanded after 2 hours of air-drying
- sand with 320-400 grade fre-cut paper, remove all sanding dust
- finish with Colourthane S-Series Clear Topcoat
- do not apply or attempt to cure at temperatures below 10°C
- relative humidity should not exceed 75% during application and before the dry to handle time Warning: Excessive builds on timber can lead to stress-cracking as the timber adjusts to its new conditions of temperature and moisture content. The recommended maximum total build is 150 microns (dry film) for the total system.
- for recommendations outside those contained in this data sheet, refer to Wattyl

Version 6, October 2010 1 of 2



COLOURTHANE SE200 CLEAR POLYURETHANE SEALER

TM6.21

APPLICATION

CONVENTIONAL SPRAY

recommended thinner Colourthane Reducer Standard

volume of thinner up to 10% fluid nozzle 1.5 - 2.0 mm

pressure to the gun...... 250 - 350 kPa (30 - 50 psi)

AIR-ASSISTED AIRLESS SPRAY

recommended thinner Colourthane Reducer Standard

volume of thinner up to 5%

fluid nozzle 0.23 - 0.28 mm (0.009- 0.11inch)

pump ratio 12 - 20 : 1 0

HVLP CONVENTIONAL

recommended thinner Colourthane Reducer Standard

volume of thinner up to 5% 0 fluid nozzle 1.5 - 2.0 mm

pressure to the gun...... 250 - 350 kPa (30 - 50 psi)

pressure to air cap 70 kPa (10 psi)

CLEANING SOLVENT L780 Industrial Universal Thinner or Colourthane Reducer Standard

Note: In warmer conditions, replace some or all of Colourthane Reducer Standard with Colourthane Reducer Slow.

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- contains 0.12% monomeric diisocyanate when mixed. Provide adequate ventilation during use. Breathing the vapour is dangerous. Avoid prolonged breathing of fumes. Where ventilation is poor or where applied by spray, use suitable respiratory equipment at all times
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

PACKAGING

Part A 4, 20 litres Part B 4, 20 litres

For the most up to date information contact Wattyl Customer Service Hotline or visit the Wattyl Website.

New Zealand Australia **CUSTOMER SERVICE HOTLINE** 132 101 0800 735 551

WEBSITE http://www.wattyl.com.au http://www.wattyl.co.nz

Wattyl, Colourthane and Craftsman are registered trademarks of Wattyl Australia Pty Ltd.

Mattyl, Colourthane and Craftsman are registered trademarks of Wattyl Australia Pty Ltd.

1. This information is important to ensure that the listed Wattyl product(s) perform according to the stated application and uses and must be followed to meet Wattyl's warranties express and implied. Wattyl advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Wattyl and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in its TDS was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl does not warrant that the information provided is current when the product is used or is wholly comprehensive.

3. For all product and non-product related information, Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl office before using the product(s). 4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product: or (b) payment of the cost of replacing the product. If coating rectification is required Wattyl Technical Services shall be contacted prior to commencement. WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)

Version 6, October 2010 2 of 2